

**Letter of Commission**

No.: -  
Date: 13 Jun 2018  
Date of arrival: 15 Jun 2018

**Test Report**

No.: 3/172-2018(E)  
Date: 18 Jun 2018

**Your Executive:** Mr. Tamás Pióker

**Our Executive:** Mrs. Czagány

**TEST REPORT**

**Applicant:** K9-Sport Kft.  
**Address:** H-2310 Szigetszentmiklós, Ipar u. 10-12.

**Tested sample:** K9 power harness with normal seam

**Date of arrival of sample:** 14 Jun 2018  
**Date of testing:** 14 Jun 2018

**Test performed:**

Tensile test [MSZ EN ISO 13934-1:2000].  
Number of test specimens: 5.  
Rate of extension: 100 mm/min. Type of device used: INSTRON 3369.  
Clamping of specimen: the artificial dog mannequin was fastened on the lower clamping, the harness on the artificial dog mannequin was fixed to the cross head.

**Test result:**

Breaking strength (N) 2377

- Notes:
- The test result relates only to the tested sample.
  - This Test Report contains 1 page, which can only be copied in full unless the written permission of the testing laboratory is obtained.
  - The testing laboratory is accredited by NAH. Accreditation number: NAH-1-1366/2016.
  - Validity of issued test report is proven by dry seal of INNOVATEXT Zrt. seen of page of it.

**INNOVATEXT**  
Textilipari Műszaki Fejlesztő  
és Vizsgáló Intézet Zrt.  
1103 Budapest, Gyömrői út 86.

  
**Kovács Andrásné**  
Head of Testing Department



European Notified  
Testing and Certification  
Body No. 1523



Member of the European  
Network of Textile  
Research Organisations



Institute of the  
International Association  
OEKO-TEX®